


- 1. INSTALL TYPE (8) KEYWAY IN LONGITUDINAL JOINT WHERE LENGTH OF REPAIR IS 3 m OR GREATER.
- 2. STANDARD WIRE FABRIC REINFORCING SHALL BE USED IN PATCHES HAVING DISTANCES BETWEEN TRANSVERSE JOINTS OF > 4.5 m.

DETAIL A

- 3. 32 mm SMOOTH EPOXY COATED DOWELS SHALL BE USED IN ALL CLASS A PAVEMENT REPAIR TRANSVERSE JOINTS.
- 4. THE ANCHORING MATERIAL (EPOXY OR POLYESTER) SHALL BE PLACED TO THE BACK OF THE PREDRILLED HOLE BEFORE INSERTING THE DOWEL OR TIE BAR.
- 5. THE DOWEL IS INSERTED INTO THE HOLE WITH A TWISTING MOTION SO THAT THE MATERIAL IN THE BACK OF THE HOLE IS FORCED UP AND AROUND THE BAR.
- 6. EXPOSED END OF DOWEL SHALL BE COATED WITH A THIN UNIFORM COAT OF GRAPHITE GREASE. IN LIEU OF GRAPHITE GREASE, THE DOWEL BAR BASKET SUPPLIER MAY PROVIDE COMPLETED BASKET UNITS PRE-DIPPED IN AN APPROVED BONDBREAKER.
- 7. REPAIR ONLY ONE LANE AT A TIME.
- 8. D = DOWEL DIAMETER (INCLUDING PROTECTIVE COATING, IF ANY).

TWO OR MORE LANES



DOWEL BASKET AND SAW CUT ONLY IF 4.5 m

1. STANDARD WIRE FABRIC REINFORCING SHALL BE USED IN PATCHES HAVING DISTANCES BETWEEN TRANSVERSE JOINTS OF > 4.5 m.


DETAIL B

225

- 2. 32 mm SMOOTH EPOXY COATED DOWELS SHALL BE USED IN ALL CLASS A PAVEMENT REPAIR TRANSVERSE JOINTS.
- 3. THE ANCHORING MATERIAL (EPOXY OR POLYESTER) SHALL BE PLACED TO THE BACK OF THE PREDRILLED HOLE BEFORE INSERTING THE DOWEL OR TIE BAR.
- 4. THE DOWEL IS INSERTED INTO THE HOLE WITH A TWISTING MOTION SO THAT THE MATERIAL IN THE BACK OF THE HOLE IS FORCED UP AND AROUND THE BAR.
- 5. EXPOSED END OF DOWEL SHALL BE COATED WITH A THIN UNIFORM COAT OF GRAPHITE GREASE. IN LIEU OF GRAPHITE GREASE, THE DOWEL BAR BASKET SUPPLIER MAY PROVIDE COMPLETED BASKET UNITS PRE-DIPPED IN AN APPROVED BONDBREAKER.
- 6. D = DOWEL DIAMETER (INCLUDING PROTECTIVE COATING, IF ANY).

ONE LANE

NON-REINFORCED AND REINFORCED PORTLAND CEMENT CONCRETE




DETAIL C THIN CIRCULAR DISK


GENERAL NOTES:

ALL DIMENSIONS SHOWN ARE IN mm UNLESS OTHERWISE NOTED.

ALL SAW CUTS SHALL BE MADE WITH A DIAMOND SAW EXCEPT THE CENTER RELIEF CUT.

FOR DETAILS OF TYPE (© JOINT, SEE STANDARD PLAN M502.05.





- 2. STANDARD WIRE FABRIC REINFORCING SHALL BE USED IN ALL PATCHES.
- 3. 32 mm EPOXY COATED DOWELS SHALL BE USED IN ALL CLASS B PAVEMENT REPAIR TRANSVERSE JOINTS.
- 4. THE ANCHORING MATERIAL (EPOXY OR POLYESTER) SHALL BE PLACED TO THE BACK OF THE PREDRILLED HOLE BEFORE INSERTING THE DOWEL OR TIE BAR.
- 5. THE TIE BAR IS INSERTED INTO THE HOLE WITH A TWISTING MOTION SO THAT THE MATERIAL IN THE BACK OF THE HOLE IS FORCED UP AND AROUND THE BAR.
- 6. REPAIR ONLY ONE LANE AT A TIME.
- 7. D = TIE BAR DIAMETER (INCLUDING PROTECTIVE COATING, IF ANY).
- 8. FINISH CONCRETE TO EXISTING PAVEMENT SURFACE LEVEL.
- 9. HOLE SHALL BE LARGE ENOUGH TO ALLOW FREE HAND TURNING OF THE BAR. BUT NOT TO EXCEED THE BAR DIAMETER BY MORE THAN 6 mm.

TWO OR MORE LANES

- 2. 32 mm EPOXY COATED DOWELS SHALL BE USED IN ALL CLASS B PAVEMENT REPAIR TRANSVERSE JOINTS.
- 3. THE ANCHORING MATERIAL (EPOXY OR POLYESTER) SHALL BE PLACED TO THE BACK OF THE PREDRILLED HOLE BEFORE INSERTING THE DOWEL OR TIE BAR.
- 4. THE TIE BAR IS INSERTED INTO THE HOLE WITH A TWISTING MOTION SO THAT THE MATERIAL IN THE BACK OF THE HOLE IS FORCED UP AND AROUND THE BAR.
- 5. D = DOWEL DIAMETER (INCLUDING PROTECTIVE COATING, IF ANY).
- 6. FINISH CONCRETE TO EXISTING PAVEMENT SURFACE LEVEL.
- 7. HOLE SHALL BE LARGE ENOUGH TO ALLOW FREE HAND TURNING OF THE BAR, BUT NOT TO EXCEED THE BAR DIAMETER BY MORE THAN 6 mm.

ONE LANE

NON-REINFORCED AND REINFORCED PORTLAND CEMENT CONCRETE

GENERAL NOTES:

ALL DIMENSIONS SHOWN ARE IN mm UNLESS OTHERWISE NOTED.

ALL SAW CUTS SHALL BE MADE WITH A DIAMOND SAW EXCEPT THE CENTER RELIEF CUT.

FOR DETAILS OF TYPE (8) JOINT, SEE STANDARD PLAN M502.05.

